

FLEECE NON-WOVEN FABRIC FLEXIBLE DMD PAPER

TEST REPORT

Thickness: 0.14MM

Properties	UNIT	STANDARD	TEST VALUE
Tensile strength MD No bending	N/10MM	270	275
Tensile strength MD After bending	N/10MM	200	215
Tensile strength TD No bending	N/10MM	200	212
Tensile strength TD After bending	N/10MM	170	187
Elongation MD	%	10	12
Elongation TD	%	15	16.8
Breakdown voltage (No bending)	KV	15	16.2
Grammage	g/m2	350	335.4
Bonding property at room temp	—	No delamination	No delamination
Conclusion: pass the test			